



# Specs

## Treatment of Areas of Rising Damp – Below Dampcourse, around Windows and Doors, Parapet walls etc.

**MAXQUICK® ROLL**

### Products required

- **MAXQUICK ROLL**

### Method

1. Prepare area to be treated by removing any loose materials ensuring a clean and sound surface.
2. Any damage to the surface should be repaired using **MAXREST**.
3. Thoroughly wet the entire surface before applying coating. Use **MAXQUICK ROLL** on previously uncoated surfaces. Single coat application.  
**MAXQUICK ROLL** is supplied a cement powder that mixes with water. This mixture is then brushed or rolled onto a pre-dampened surface.
4. Once coated the surface should be allowed minimum 3 days (72 hours) before final paint or texture coating is applied.
5. **Note: MAXQUICK ROLL** is not suitable for static/hydrostatic water pressure, It is recommended that the **MAXSEAL** range be used in this situation

*Maxquick Roll is ideal for use under Morrocca & other acrylic textured coatings and painted finishes to provide a dry surface.*



To prevent flaking, peeling and dis-colouration to painted surfaces.



Here rising damp is causing paint to blister on the bottom course below the dampcourse.



# Specs



**SwepDri International Pty Ltd**

ABN: 90 003 944 903

*Waterproofing and Construction Products*



**National Hotline**

**1300 303 301**

**National Distributors**

PO BOX 694 PADSTOW NSW  
3 Watson Road PADSTOW  
2211 NSW AUSTRALIA

**National Faxline**

**1300 369 932**